

## DYWIDAG Bonded Post-Tensioning Systems using Strands





## Contents

---

Contents.....	3
DYWIDAG Post-Tensioning Systems.....	4
Standard Strands.....	6
Corrugated Duct.....	7
PE/PP Round Duct.....	8
ETA Approvals.....	9
Anchorage.....	10
Overview.....	13
Installation .....	16
Stressing.....	18
Grouting.....	19
Multiplane Anchorage MA with Helix Reinforcement (Minimum Anchor Body Dimensions).....	20
Multiplane Anchorage MA without Helix Reinforcement .....	22
Plate Anchorage SD.....	24
Plate Anchorage ED .....	25
Coupler R.....	26
Coupler D.....	27
Loop Anchorage HV.....	28
Bond Head Anchorage HL/HR .....	29
Coupler M/ME (Floating Anchorage Block) .....	30
Flat Multiplane Anchorage FMA.....	31
Equipment Overview .....	32
Calculation of Elongation .....	36
References .....	38
Addresses.....	46

## DYWIDAG Post-Tensioning Systems

DYWIDAG Post-Tensioning Systems are world renowned for reliability and performance, most suitable for all applications in post-tensioned construction. They embrace the whole spectrum from bridge construction, buildings, to civil applications, above and underground.

The first ever structure built with a prototype DYWIDAG Post-Tensioning System using Bars was the arch-bridge Alsleben (Germany) in 1927. From that time on DYWIDAG has continuously improved its systems to keep up with the growing demand of modern construction technology. In addition to the traditional post-tensioning system using bars, that is mainly geared towards geotechnical applications, building rehabilitation and strengthening, DSI offers a complete product line in strand post-tensioning (bonded, unbonded and external) as well as stay-cables being able to fully serve the post-tensioning construction.

DYWIDAG Post-Tensioning Systems have always combined highest safety and reliability standards with most economical efficiency in their research and development.

Dependable corrosion protection methods of the DYWIDAG Post-Tensioning Systems contribute to the longevity of modern construction. High fatigue resistance is achieved with optimized material selection and cautious detailing of all the components especially in their system assembly.

We look back on many years of valuable experience in the field of post-tensioning which leads to our extremely versatile product range that offers economical solutions for practically any problem. This includes our highly developed, most sophisticated equipment which is easy to operate in all phases beginning with assembly, installation, stressing and finally grouting.

DYWIDAG Post-Tensioning Systems are being developed and maintained by DYWIDAG-Systems International and are serviced and distributed by a worldwide network of subsidiaries. Our systems comply with the international specifications and recommendations (ASTM, AASHTO, BS, Eurocode, DIN, Austrian Code, SIA, FIP, fib, EOTA, etc.). The American construction market demands a product range that is described in separate brochures. The quality of the DSI products and services is in full compliance with ISO 9001.

### DSI Scope:

- consulting
- design and shop-drawing engineering
- manufacturing and supply
- installation or training and/or supervision of installation
- inspection and maintenance



## DYWIDAG Post-Tensioning Systems



## Standard Strands

Strands are made from 7 individual cold-drawn wires, 6 helically wound outer wires and one center wire (king wire).

The mechanical properties of the strand as well as corrosion protection properties are most important to DSI. Strands can be supplied either bare, galvanized or epoxy-coated without any loss in strength including the wedge anchorage.

For a maximum in corrosion protection we offer electrically isolated systems using polyethylene (PE) or polypropylene (PP) ducts. See also page 8.



Strands are usually packaged in so-called coils that can weigh up to 3.5 tons.



## Construction Joint

D = draining


V = vent

G = grouting

C = coupling

S = stressing

P = post-grouting



## Technical Data

Type	13 mm (0.5")		15 mm (0.6")		15 mm (0.62")	
Code	ASTM A 416	prEN 10138	ASTM A 416	ASTM A 416	prEN 10138	prEN 10138
Specification	Grade 270	BS 5896	Grade 250	Grade 270	BS 5896	BS 5896
Yield Strength $f_{p0.1k}$	N/mm <sup>2</sup>	1,670 <sup>1)</sup>	1,640 <sup>2)</sup>	1,550 <sup>1)</sup>	1,670 <sup>1)</sup>	1,560 <sup>2)</sup>
Ultimate Strength $f_{pk}$	N/mm <sup>2</sup>	1,860	1,860	1,725	1,860	1,770
Nominal Diameter	mm	12.70	12.90	15.20	15.24	15.70
Cross-Sectional Area	mm <sup>2</sup>	98.71	100.00	139.40	140.00	150.00
Weight	kg/m	0.775	0.785	1.094	1.102	1.180
Ultimate Load	kN	183.7	186.0	240.2	260.7	265.5
Modulus of Elasticity	N/mm <sup>2</sup>			~195,000		
Relaxation <sup>3)</sup> after 1,000 h at 0.7 x Ultimate Strength $f_{pk}$	%			max. 2.5		

1) yield measured at 1% effective elongation

2) yield measured at 0.1% residual elongation

3) applicable for relaxation class 2 according to Eurocode prEN 10138/BS 5896: or low relaxation complying with ASTM A 416, respectively.

## Corrugated Duct

Metal ducts represent the most economical means to create a void for tensile elements. These thin-walled (0.25 - 0.60 mm), ribbed sheet metal ducts provide a fair secondary corrosion

protection with excellent bond behavior between tendon and concrete. Primary corrosion protection is provided by the alkalinity of grout and concrete.




### Dimensions of Corrugated Duct (Standard Sizes)

Tendon Type		Sheathing	
0.5"	0.6"/0.62"	I.D.	O.D.
		mm	mm
5901	6801	25	30
5902	6802	40	45
5904	6803	45	50
5905	6804	50	55
5907	6805	55	60
5909	6807	60	65
5912	6809	70	75
5915	6812	80	85
5920	6815	85	90
5927	6819	95	100
5932	6822	100	105
5937	6827	110	117
-	6831	120	127
-	6837	130	137
-	6843	140	147
-	6849	150	157
-	6855	160	167

The tendon type number (e.g. 5901, 6801) is composed as follows: the first digit (5 or 6) identifies the nominal strand diameter in tenth of inches, i.e. 0.5" or 0.6"/0.62", the last two digits (...01) reference the number of used strands (= 1 strand).

The second digit is an internal code. As regards the 0.6" tendon types, the accessories fit both Grade 250 (GUTS 1770 N/mm<sup>2</sup>) and Grade 270 (GUTS 1860 N/mm<sup>2</sup>) strands.

Tendon Type		Support Distances up to <sup>1)</sup> mm	Woble Coefficent rad/m	Friction Coefficient rad <sup>-1</sup>
0.5"	0.6"/0.62"			
5901	6801	1.0	5 x 10 <sup>-3</sup>	0.19
5902	6802	1.0	5 x 10 <sup>-3</sup>	0.19
5904	6803	1.0	5 x 10 <sup>-3</sup>	0.19
5905	6804	1.0	5 x 10 <sup>-3</sup>	0.19
5907	6805	1.0	5 x 10 <sup>-3</sup>	0.19
5909	6807	1.5	5 x 10 <sup>-3</sup>	0.19
5912	6809	1.5	5 x 10 <sup>-3</sup>	0.19
5915	6812	1.5	5 x 10 <sup>-3</sup>	0.19
5920	6815	1.8	5 x 10 <sup>-3</sup>	0.19
5927	6819	1.8	5 x 10 <sup>-3</sup>	0.19
5932	6822	1.8	5 x 10 <sup>-3</sup>	0.19
5937	6827	1.8	5 x 10 <sup>-3</sup>	0.19
-	6831	1.8	5 x 10 <sup>-3</sup>	0.19
-	6837	1.8	5 x 10 <sup>-3</sup>	0.19
-	6843	1.8	5 x 10 <sup>-3</sup>	0.19
-	6849	1.8	5 x 10 <sup>-3</sup>	0.19
-	6855	1.8	5 x 10 <sup>-3</sup>	0.19



1) 1.0-1.8 m with stiffening, e.g. with PE tube; 0.8-1.5 m with strengthened duct  
In tendon section with minimum radius of curvature a distance of 0.6-1.2 m shall apply.

## PE/PP Round Duct

Thick-walled polyethylene/polypropylene plastic ducts provide long-term secondary corrosion protection especially in aggressive environments such as in case of waste water treatment plants, acid tanks, silos or structures exposed to de-icing salts.

DYWIDAG-Systems International offers polyethylene/polypropylene ducts in straight lengths up to  $\approx 24$  m for all sizes. Standard shipping length is  $\approx 12$  m. Longer lengths in coils are available for all sizes except 130 mm.



### Dimensions of Round Corrugated PE/PP Duct (Standard Size)

Tendon Type		Sheathing		Wall Thickness
0.5"	0.6"/0.62"	I.D.	O.D.	mm
5907	6805	48	59	2.0
5909	6807	59	73	2.0
5912	6809	76	91	2.5
5915	6812	76	91	2.5
5920	6815	85	100	2.5
5927	6819	100	116	3.0
5932	6822	100	116	3.0
5937	6827	115	135	3.5
-	6837	130	151	4.0



## Flat PE/PP Duct

Tendon Type		A	B	a	b	Wall Thickness
0.5"	0.6"	mm	mm	mm	mm	mm
5902	6802	52.5	36.5	37.5	21.5	2.0
5904	6803	85.5	36.0	71.0	21.0	2.0
5905	6804	90.0	40.0	75.5	25.0	2.0
5907	6805	105.0	40.0	91.0	22.0	2.0

# ETA Approvals



Osterreichisches Institut für Bautechnik  
Schenkenstrasse 4 - 1010 Vienna - Austria  
T +43 1 533 65 50 - F +43 1 533 64 23  
mail@oib.or.at - www.oib.or.at

**European technical approval** **ETA-03/0036**

English translation, the original version is in German

Handelsbezeichnung Trade name	SUSPA/DSI – MonolitzenSpannverfahren ohne Verbund mit 1 bis 5 Monolitzen SUSPA/DSI – Unbonded Monostrand System with 1 to 5 Monostrands
Zulassungsinhaber Holder of approval	DYWIDAG-Systems International GmbH Destouchesstrasse 68 80796 München Deutschland
Zulassungsgegenstand und Verwendungszweck Generic type and use of construction product	Spannsystem für das Vorspannen von Tragwerken mit Monolitzen ohne Verbund für Beton Post-tensioning kit for prestressing of structures with unbonded monostrands for concrete
Geltungsdauer vom Validity from bis zum to	30.06.2013 29.06.2018
Herstellwerk Manufacturing plant	DYWIDAG-Systems International GmbH Max-Planck-Ring 1 40764 Langenfeld Deutschland
Diese Europäische technische Zulassung umfasst: This European technical approval contains:	38 Seiten einschließlich 15 Anhängen 38 Pages including 15 Annexes
Diese Europäische technische Zulassung ersetzt: This European technical approval replaces:	ETA-03/0036 mit Geltungsdauer vom 01.04.2009 bis zum 31.03.2014 ETA-03/0036 with validity from 01.04.2009 to 31.03.2014

**EOTA** European Organisation for Technical Approvals  
Europäische Organisation für Technische Zulassungen  
Organisation Européenne pour l'Agrement Technique

Construction products with an European Technical Approval (ETA) meet all essential demands given in the Construction Products Regulation (CPR).

The ETA holder is authorized to apply the CE-marking (Conformité Européenne) on his product. The CE-marking certifies the conformity with the technical specification and is the basis for the free movement of goods within the EU member states.

DSI is proud to have European Technical Approvals for its PT-systems with bars, bonded strands and unbonded strands.



Osterreichisches Institut für Bautechnik  
Schenkenstrasse 4 - 1010 Vienna - Austria  
T +43 1 533 65 50 - F +43 1 533 64 23  
mail@oib.or.at - www.oib.or.at

**European technical approval** **ETA-13/0815**

English translation, the original version is in German

Handelsbezeichnung Trade name	DYWIDAG-Lite DYWIDAG Strand
Zulassungsinhaber Holder of approval	DYWIDAG-Systems International GmbH Destouchesstrasse 68 80796 München Deutschland
Zulassungsgegenstand und Verwendungszweck Generic type and use of construction product	LitzenSpannverfahren mit 3 bis 55 Litzen für das Vorspannen von Tragwerken im Verbund Bonded post-tensioning kit for prestressing of structures with 3 to 55 strands
Geltungsdauer vom Validity from bis zum to	28.06.2013 27.06.2018
Herstellwerk Manufacturing plant	DYWIDAG-Systems International GmbH Max-Planck-Ring 1 40764 Langenfeld Deutschland
Diese Europäische technische Zulassung umfasst: This European technical approval contains:	58 Seiten einschließlich 35 Anhängen 58 Pages including 35 Annexes

**EOTA** European Organisation for Technical Approvals  
Europäische Organisation für Technische Zulassungen  
Organisation Européenne pour l'Agrement Technique



Service d'études sur les transports, les routes et leurs aménagements  
139 rue de Paris  
77171 Nointel  
Tel : +33 (0)1 60 52 31 31  
Fax : +33 (0)1 60 52 31 49

**European Technical Approval ETA-13/0979**  
(English language translation, the original version is in French language)

Nom commercial : Trade name :	DYwidag External and Internal unbonded Strand Post-Tensioning System
Détenteur de l'ATE : Holder of approval :	DYWIDAG-Systems International GmbH Destouchesstrasse 68 80796 München DEUTSCHLAND
Type générique et utilisation prévue du produit de construction :	Procédé de précontrainte par post-tension DYWIDAG avec câble extérieur et intérieur non adhérant de 3 à 37 tresses (140 et 150 m <sup>2</sup> ). DYWIDAG External and Internal unbonded Strand Post-Tensioning System for 3 to 37 Strands (140 and 150 m <sup>2</sup> ).
Valid from: to:	27.06.2013 27.06.2018
Producteur du procédé : Kit manufacturer :	DYWIDAG-Systems International GmbH Max-Planck-Ring 1 40764 Langenfeld DEUTSCHLAND
Le présent agrément technique européen contient : This European Technical Approval contains :	50 pages comprenant 27 pages de dessins faisant partie intégrante du document. 50 pages including 27 pages of drawings which form an integral part of the document.

**EOTA** Organisation pour l'Agrement Technique Européen  
European Organisation for Technical Approvals

## Anchorage

### Multiplane Anchorage MA

The two-part multiplane anchorage is primarily used for longitudinal tendons in beams and bridges.

The wedge plate and the multiplane anchor body with usually three load transfer planes introduce the pre-stressing force continuously into the member with minimal front area.

The MA anchorage can be installed with and without helix reinforcement.

The separation of anchor body and wedge plate makes it possible to insert the strand after casting the concrete. The wedge plate self-centers on the anchor body providing consistent assembly and installation as well as trouble-free stressing.



Stressing Anchorage	Dead End Anchorage Accessible	Dead End Anchorage not Accessible	Ultimate Load kN
✓	✓	✓	from 1,201 to 15,345

### Plate Anchorage SD

The single unit plate anchorage is designed for plate structures as well as transverse tendons in bridges. Small edge and center distances allow for an economical anchorage layout in condensed situations.



Stressing Anchorage	Dead End Anchorage Accessible	Dead End Anchorage not Accessible	Ultimate Load kN
✓	✓	✓	from 721 to 2,511

### Plate Anchorage Type ED

The two-part plate anchorage can be used in slabs and similar structures, e.g. transversal prestressing in bridge decks. The wedge plate self-centers on the anchor plate providing consistent assembly and installation as well as trouble-free stressing.



Stressing Anchorage	Dead End Anchorage Accessible	Dead End Anchorage not Accessible	Ultimate Load kN
✓	✓	✓	from 721 to 1.395

## Anchorage

### Coupler R

Coupler R is designed to couple on to already installed and stressed tendons. The coupler consists of a multiplane anchor body and a coupler wedge plate where the strands are overlapped. The continuing strands can be installed easily and independently.



Fixed Coupler	Floating Coupler	Ultimate Load kN
✓	-	from 1,201 to 10,323

### Coupler D

To lengthen unstressed tendons, e.g. in segmental bridge construction, coupler D is put to use. The splice chuck consists of two spring-loaded wedges that connect two strands individually.



Fixed Coupler	Floating Coupler	Ultimate Load kN
-	✓	from 721 to 10,323

### Loop Anchorage HV

Often used in large plate-shaped structures, walls in off-shore structures or LNG tanks with generally static loadings. The 180° loop should be positioned in the center of the tendon to allow for non-slippage during simultaneous two-end stressing.




Stressing Anchorage	Dead End Anchorage Accessible	Dead End Anchorage not Accessible	Ultimate Load kN
-	-	✓	from 721 to 6,138

## Anchorage

### Bond Head Anchorage HL/HR


Primarily used with prefabricated tendons, it is also possible to fabricate this anchorage on site. The strand wires are plastically deformed to ensure a safe load transfer up to ultimate capacity in the area of the bond head proven in static as well as in dynamic applications. Depending on the boundary conditions either a rather flat or a bulky bond head anchorage pattern is available.



### Coupler M/ME (Floating Anchorage Block)


Rotation symmetric structures (water tanks, digestor tanks, large pipes or dome shells) that require circumferential post-tensioning are the principal applications for the floating coupler M/ME. The tendon anchorage consists of an anchorage block with wedge holes on both sides to accept bare or greased and sheathed strands.

The strands actually overlap in the block and use the belt-buckle principle. The ring-tendon is very compact and requires a very small pocket only.



### Flat Multiplane Anchorage FMA

The Flat Multiplane Anchorage of max. 5-0.62" strands in one plane to deviate into one oval duct is designed to be installed in thin members such as transverse post-tensioning of the top slab of box-girder bridges and prestressed flat slabs.



## Overview

### Tendon Type 59...


Anchorage Type 59...	01	02	03	04	05	06	07	08	09	12	15	20	27	32	37
Multiplane Anchorage MA							x		x	x	x	x	x	x	x
Plate Anchorage SD			x	x	x	x	x	x	x	x					
Plate Anchorage Type ED			x	x	x	x	x								
Coupler R									x	x	x	x	x	x	x
Coupler D			x	x	x		x		x	x	x	x	x	x	x
Loop Anchorage HV			x	x	x	x	x	x	x	x	x	x	x	x	
Bond Head Anchorage HL/HR			x	x	x		x		x	x	x	x	x		
Flat Multiplane Anchorage FMA			x	x	x										


Other sized tendons on request

### Tendon Type 68...

Anchorage Type 68...	01	02	03	04	05	06	07	08	09	10	12	15	19	22	27	31	37	43	49	55
Multiplane Anchorage MA					x		x		x		x	x	x	x	x	x	x	x	x	
Plate Anchorage SD			x	x	x	x	x	x	x											
Plate Anchorage Type ED			x	x	x															
Coupler R					x		x		x		x	x	x	x	x	x	x	x		
Coupler D			x	x	x		x		x		x	x	x	x	x	x	x	x		
Loop Anchorage HV			x	x	x	x	x		x		x	x	x	x						
Bond Head Anchorage HL/HR			x	x	x		x		x		x	x	x	x						
Coupler M and ME	x	x	x		x		x		x	x	x	x	x	x						
Flat Multiplane Anchorage FMA	x		x	x																

Other sized tendons on request






**Slab with unbonded  
Strand Tendons**

**External  
Wire Tendons**

**Internal DYWIDAG  
Strand Tendons**




## Installation

DYWIDAG-Systems International has developed three different methods to insert strands into ducts. The selection of the insertion method depends on the boundary conditions of the structure and the job site.



### Method 1: Pushing



To push strands into the duct on the job site is very economical and can be done either before or after casting the concrete. The pushing equipment can be installed remotely and connected flexibly to the insertion point. DSI strand pushers provide relatively high speed of up to 8 m/s and require minimal operating personnel of only two men. These advantages make this method the preferred standard for strand installation.



## Installation

### Method 2: Pulling

To install strands while pulling them into the duct can be very efficient in special structures, for example where the loop anchorage is used. In normal cases the whole bundle of strands is pulled through winching with a steel cable.



### Method 3: Pre-Assembled Tendons

The prefabrication of tendons either in the shop or in the field can also be very economical, especially with shorter tendons and short shipping distances. Special uncoilers or hydraulic winches are necessary to properly install the tendons in the structure.



## Stressing

DYWIDAG has developed a series of jacks, rams and hydraulic pumps in order to reach the target stressing load. The necessary versatility is provided by changing devices that make one unit adaptable for many different tendon sizes. DYWIDAG Equipment is designed to cover a wide spectrum of applications with jack capacities ranging from 250 kN up to 15,000 kN.

DYWIDAG rams are highly sophisticated, but still convenient to operate. They employ inner tube bundles with automatic gripping devices that guide the strand safely through the inside of the ram. This feature allows the stressing operation to be controlled with the highest degree of reliability as well as minimal wedge seating losses by benefiting from the power seating option. Power seating is a way of hydraulically pressing in the wedges with a predefined load individually and simultaneously rather

than relying simply on friction seating. DYWIDAG rams also make it possible to overstress and release the tendon to compensate for friction losses and maximize the stress level over the tendon length.

Every ram has a pressure relief valve for safety reasons that activates to limit hydraulic pressure should the hydraulic pump malfunction. To further verify the stressing operation an additional gauge port is provided directly on the ram.

Stressed tendons can be destressed with special wedges and a special ram configuration. Hydraulic pumps can be equipped with a convenient remote control device. Further information concerning the equipment is provided on page 30 and following.



Hydraulic Pump with a Remote Control



## Grouting

The durability of post-tensioned construction depends mainly on the success of the grouting operation. The hardened cement grout provides bond between concrete and tendon as well as primary long-term corrosion protection for the prestressing steel.

DYWIDAG has developed a grouting operation that is based on thixotropic and highly plasticized grout, and utilizes durable grouting equipment. Advanced methods such as pressure grouting, post-grouting and vacuum grouting are all results of many years of development.

Grouting is always done from a low-point of the tendon. This can be one of the anchorages where a grout cap with grout hose is the port for the grout or along the tendon utilizing an intermediate grout saddle. All grouting components are threaded for easy, fast and positive connection.



Venting Operation




Mixing and Grouting Unit



Vacuum Grouting




## Multiplane Anchorage MA with Helix Reinforcement (Minimum Anchor Body Dimensions)



### Technical Data

Type 0.5" $f_{pk}$ 1860 N/mm <sup>2</sup>	Ultimate Load $\varnothing$ 12.9 mm (186 kN per strand)	Type 0.6"/0.62" $f_{pk}$ 1860 N/mm <sup>2</sup>	Ultimate Load $\varnothing$ 15.7 mm (279 kN per strand)	$\varnothing$ d mm	$\varnothing$ a mm	e* mm	j mm	m mm
5907	1,302	6805	1,395	117	150	47	90	240
5909	1,674	6807	1,953	130	170	52	100	210
5912	2,232	6809	2,511	145	190	52	125	280
5915	2,790	6812	3,348	170	220	55	180	350
5920	3,720	6815	4,185	190	250	60	200	390
5927	5,022	6819	5,301	210	280	68	220	430
5932	5,952	6822	6,138	220	305	73	220	550
5937	6,882	6827	7,533	240	330	80	240	550
-	-	6831	8,649	270	385	80	350	570
-	-	6837	10,323	270	420	95	350	570
-	-	6843	11,997	320	465	110	380	950
-	-	6849	13,671	340	510	120	420	780
-	-	6855	15,345	340	510	120	420	780

## Multiplane Anchorage MA with Helix Reinforcement (Minimum Anchor Body Dimensions)



### Details of the Anchorage Zone for 34 N/mm<sup>2</sup> (cube) / 28 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

Ø12.9 mm, Ultimate Load 186 kN						
Type 0.5"	Distances of the anchorages		Additional Reinforcement Helix <sup>2)</sup>			
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distance mm	Edge Distance <sup>1)</sup> mm	Ø da mm	min l* mm	n*	ds mm
5907	230	135	170	225	4	12
5909	260	150	190	260	4	12
5912	290	165	220	310	5	12
5915	320	180	240	410	7	12
5920	370	205	280	465	8	12
5927	425	235	350	470	8	16
5932	460	250	360	500	8.5	16
5937	500	270	390	525	9	16

1) in case of 30 mm concrete cover

2) additional surface reinforcement acc. to ETA-13/0815 is required.

The values for the anchorage zones  
are based on European Technical Approval ETA-13/0815.  
Center/edge distances and data for additional reinforcement for  
other actual concrete strengths can be found on  
[www.dywidag-systems.com](http://www.dywidag-systems.com)  
Max. prestressing load 75 % of ultimate  
load (short-term overstressing to 80 % is permissible)  
The respective standards and regulations valid at the place of use  
shall be complied with.


Ø15.2/15.7 mm, Ultimate Load 261/279 kN						
Type 0.62"	Distances of the anchorages		Additional Reinforcement Helix <sup>2)</sup>			
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distance mm	Edge Distance <sup>1)</sup> mm	Ø da mm	min l* mm	n*	ds mm
6805	235	140	185	225	4	12
6807	280	160	220	260	4	14
6809	305	175	250	310	5	14
6812	350	195	265	410	7	14
6815	390	215	310	465	8	14
6819	435	240	375	470	8	16
6822	470	255	370	500	8.5	16
6827	520	280	430	525	9	16
6831	640	340	560	615	9	20
6837	700	370	620	615	9	20
6843 <sup>3)</sup>	640	340	530	675	10	20
6849 <sup>3)</sup>	680	360	550	675	10	20
6855 <sup>3)</sup>	710	375	580	700	11	20

1) in case of 30 mm concrete cover

2) additional surface reinforcement acc. to ETA-13/0815 is required.

3) for that size only concrete strength 43/53 N/mm<sup>2</sup>.


## Multiplane Anchorage MA without Helix Reinforcement



### Technical Data

Type 0.5" $f_{pk}$ 1860 N/mm <sup>2</sup>	Ultimate Load <b>Ø 12.9 mm</b> (186 kN per strand)	Type 0.6"/0.62" $f_{pk}$ 1860 N/mm <sup>2</sup>	Ultimate Load <b>Ø 15.7 mm</b> (279 kN per strand)	$\varnothing$ d mm	$\varnothing$ a mm	e* mm	j mm	m mm
5907	1,302	6805	1,395	117	150	47	90	240
5909	1,674	6807	1,953	130	170	52	100	210
5912	2,232	6809	2,511	145	190	52	125	280
5915	2,790	6812	3,348	170	220	55	180	350
5920	3,720	6815	4,185	190	250	60	200	390
5927	5,022	6819	5,301	210	280	68	220	430
5932	5,952	6822	6,138	220	305	73	220	550

## Multiplane Anchorage MA without Helix Reinforcement



### Details of the Anchorage Zone for 34 N/mm<sup>2</sup> (cube) / 28 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

Ø12.9 mm, Ultimate Load 186 kN							Ø15.2/15.7 mm, Ultimate Load 261/279 kN								
Type 0.5"	Distances of the anchorages		Additional Reinforcement Stirrups <sup>2)</sup>					Type 0.6"/0.62"	Distances of the anchorages		Additional Reinforcement Stirrups <sup>2)</sup>				
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distance mm	Edge Distance <sup>1)</sup> mm	x/y	i	n*	ds	f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distance mm	Edge Distance <sup>1)</sup> mm	x/y	i	n*	ds		
5907	250	145	230	50	5	16	6805	255	150	240	50	5	16		
5909	280	160	260	50	6	16	6807	300	170	280	50	6	16		
5912	320	180	290	50	6	16	6809	335	190	305	50	6	16		
5915	350	195	300	45	8	16	6812	380	210	320	45	8	16		
5920	400	220	360	50	8	16	6815	425	235	380	55	8	20		
5927	465	255	400	55	8	20	6819	475	260	410	55	8	20		
5932	500	270	425	50	10	20	6822	510	275	430	50	10	20		

1) in case of 30 mm concrete cover

2) stirrup dimensions must be adhered to exactly

1) in case of 30 mm concrete cover

2) stirrup dimensions must be adhered to exactly


The values for the anchorage zones are based on European Technical Approval ETA-13/0815.

Center/edge distances and data for additional reinforcement for other actual concrete strengths can be found on [www.dywidag-systems.com](http://www.dywidag-systems.com)

Max. prestressing load 75 % of ultimate load (short-term overstressing to 80 % is permissible).


The respective standards and regulations valid at the place of use shall be complied with.

## Plate Anchorage SD



### Technical Data

Type 0.5"	Ultimate Load Ø 12.9 mm	Type 0.6"/0.62"	Ultimate Load Ø 15.7 mm	A	B	C	D
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	(186 kN per strand)	f <sub>pk</sub> 1860 N/mm <sup>2</sup>	(279 kN per strand)	mm	mm	mm	mm
5904	744	6803	837	125	140	41	200
5905	930	6804	1,116	135	160	41	200
5907	1,302	6805	1,395	150	180	40	300
5909	1,674	6807	1,953	170	215	44	270
5912	2,232	6809	2,511	190	245	48	325



### Details of the Anchorage Zone for 30 N/mm<sup>2</sup> (cube) / 24 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

Ø12.9/15.2/15.7 mm, Ultimate Load 186/261/279 kN											
Type 0.5"	Type 0.6"/0.62"	Distances of the anchorages				Additional Reinforcement					
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distance mm	Edge Distance <sup>1)</sup> mm	E mm	F mm	n	e mm	G mm	n	g mm	
5904	6803	170/250	105/145	—	—	—	—	285	6	12	
5905	6804	190/290	115/165	—	—	—	—	285	6	12	
5907	6805	215/320	130/180	160	275	5	12	340	7	12	
5909	6807	250/370	145/205	190	275	5	14	340	7	12	
5912	6809	280/420	160/230	220	330	6	14	370	7	12	


1) in case of 30 mm concrete cover

The values for the anchorage zones are based on European Technical Approval ETA-13/0815.

Max. prestressing load 75 % of ultimate load (short-term overstressing to 80 % is permissible).

The respective standards and regulations valid at the place of use shall be complied with.

## Plate Anchorage ED



### Technical Data

Type 0.5"	Ultimate Load <b>Ø 12.9 mm</b>	Type 0.6"/0.62"	Ultimate Load <b>Ø 15.7 mm</b>	Ø d	Ø a	e*	c	m
$f_{pk} 1860$	(186 kN per strand)	$f_{pk} 1860$	(279 kN per strand)					
N/mm <sup>2</sup>	kN	N/mm <sup>2</sup>	kN	mm	mm	mm	mm	mm
5904	744	6803	837	110	165	47	30	170
5905	930	6804	1,116	110	165	47	30	170
5907	1,302	6805	1,395	135	190	47	30	280

### Details of the Anchorage Zone for 35 N/mm<sup>2</sup> (cube) / 28 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

Ø12.9/15.2 mm, Ultimate Load 186/261 kN							
Type 0.5"	Type 0.6"	Distances of the anchorages		Additional Reinforcement Helix			
$f_{pk} 1860$	$f_{pk} 1860$	Center Distance	Edge Distance <sup>1)</sup>	Ø da	min l*	$n^*$	ds
N/mm <sup>2</sup>	N/mm <sup>2</sup>	mm	mm	mm	mm		
5904	6803	190	115	150	175	5	14
5905	6804	215	130	180	195	5	14
5907	6805	240	140	205	195	5	14

1) in case of 30 mm concrete cover

Ø15.7 mm, Ultimate Load 279 kN							
Type 0.62"	Distances of the anchorages		Additional Reinforcement Helix				
$f_{pk} 1860$	Center Distance	Edge Distance <sup>1)</sup>	Ø da	min l*	$n^*$	ds	
N/mm <sup>2</sup>	mm	mm	mm	mm			
6803	200	120	150	175	5	14	
6804	225	135	180	195	5	14	
6805	250	145	205	195	5	14	

1) in case of 30 mm concrete cover


The values for the anchorage zones are based on European Technical Approval ETA-06/0022.

Center/edge distances and data for additional reinforcement for other actual concrete strengths and further assistance can be found on [www.dywidag-systems.com](http://www.dywidag-systems.com).

Max. prestressing load 75 % of ultimate load (short-term overstressing to 80 % is permissible). The respective standards and regulations valid at the place of use shall be complied with.



## Coupler R



### Technical Data

Type	Ultimate Load	$\emptyset d$	$\emptyset F_R$	$h_1$	$l_1$	Type	Ultimate Load	$\emptyset d$	$\emptyset F_R$	$h_1$	$l_1$
<b>0.5"</b>	<b><math>\emptyset 12.9 \text{ mm}</math></b>	$\emptyset d$	$\emptyset F_R$	$h_1$	$l_1$	<b>0.6"/0.62"</b>	<b><math>\emptyset 15.2/15.7 \text{ mm}</math></b>	$\emptyset d$	$\emptyset F_R$	$h_1$	$l_1$
$f_{pk}1860$	(186 kN per strand)					$f_{pk}1860$	(261/279 kN per strand)				
N/mm <sup>2</sup>	kN	mm	mm	mm	mm	N/mm <sup>2</sup>	kN	mm	mm	mm	mm
5909	1,674	224	168	105	350	6805	1,395	207	152	105	460
5912	2,232	224	172	105	350	6807	1,953	207	152	105	370
5915	2,790	246	191	105	500	6809	2,511	224	168	105	350
5920	3,720	264	215	110	450	6812	3,348	246	188	105	500
5927	5,022	320	262	120	570	6815	4,185	264	207	110	450
5932	5,952	340	279	125	640	6819	5,301	289	224	120	570
5937	6,882	380	318	135	660	6822	6,138	340	276	125	640
						6827	7,533	380	314	135	660
						6831	8,649	435	370	158	870
						6837	10,323	435	370	158	870



### Details of the Coupler Zone

<b><math>\emptyset 12.9 \text{ mm, Ultimate Load } 186 \text{ kN}</math></b>				<b><math>\emptyset 15.2/15.7 \text{ mm, Ultimate Load } 261/279 \text{ kN}</math></b>			
Type	Minimum Center Distance of Coupler R	Minimum Edge Distance of Coupler R	Length of Space for Installation	Type	Minimum Center Distance of Coupler R	Minimum Edge Distance of Coupler R	Length of Space for Installation
<b>0.5"</b>				<b>0.6"/0.62"</b>			
$f_{pk}1860$				$f_{pk}1860$			
N/mm <sup>2</sup>	kN	mm	mm	N/mm <sup>2</sup>	kN	mm	mm
5909	330	190	1,500	6805	310	180	1,500
5912	330	190	1,500	6807	310	180	1,500
5915	350	200	1,500	6809	330	190	1,500
5920	370	210	1,500	6812	350	200	1,500
5927	430	240	1,700	6815	370	210	1,500
5932	450	250	1,700	6819	400	225	1,700
5937	490	270	1,700	6822	450	250	1,700
				6827	490	270	1,700
				6831	550	300	2,000
				6837	550	300	2,000

The center/edge distances and additional reinforcement for Coupler R are identical with those of the corresponding MA-anchorage.

Due to geometrical constraints the center/edge distances must not fall below the minimum values given in the tables.

## Coupler D




### Technical Data

Type 0.5" $f_{pk} 1860$ N/mm <sup>2</sup>	Ultimate Load $\varnothing 12.9 \text{ mm}$ (186 kN per strand) kN	Type 0.6"/0.62" $f_{pk} 1860$ N/mm <sup>2</sup>	Ultimate Load $\varnothing 15.2/15.7 \text{ mm}$ (261/279 kN per strand) kN	A mm	M mm	$\varnothing D_i$ mm
-	-	6803	837	150	900	100
5904	744	6804	1,116	200	600	110
5905	930	6805	1,395	250	900	120
5907	1,302	6807	1,953	300	900	125
5909	1,674	6809	2,511	350	900	140
5912	2,232	6812	3,348	450	900	160
5915	2,790	6815	4,185	500	900	180
-	-	6819	5,301	550	940	200
5920	3,720	6822	6,138	700	940	225
5927	5,022	6827	7,533	700	940	225
5932	5,952	6831	8,649	800	940	250
5937	6,882	6837	10,323	800	940	250

### Details of the Coupler Zone


$\varnothing 12.9/15.2/15.7 \text{ mm, Ultimate Load 186/261/279 kN}$				
Type 0.5" $f_{pk} 1860$ N/mm <sup>2</sup>	Type 0.6"/0.62" $f_{pk} 1860$ N/mm <sup>2</sup>	Center Distances Coupler to Coupler mm	Center Distances Duct to Coupler mm	
-	6803	180		135
5904	6804	195		150
5905	6805	210		160
5907	6807	220		170
5909	6809	245		195
5912	6812	270		210
5915	6815	300		235
-	6819	325		255
5920	6822	365		280
5927	6827	375		295
5932	6831	420		325
5937	6837	420		335

## Loop Anchorage HV



### Technical Data

Type	Ultimate Load	Type	Ultimate Load	ID <sub>1</sub>	ID <sub>2</sub>
0.5"	Ø 12.9 mm	0.6"/0.62"	Ø 15.7 mm	ID <sub>1</sub>	ID <sub>2</sub>
f <sub>pk</sub> 1860	(186 kN per strand)	f <sub>pk</sub> 1860	(279 kN per strand)		
N/mm <sup>2</sup>	kN	N/mm <sup>2</sup>	kN	mm	mm
5904	744	6803	837	50	40
5905	930	6804	1,116	55	45
5907	1,302	6805	1,395	60	50
5909	1,674	6807	1,953	75	60
5912	2,232	6809	2,511	85	75
5915	2,790	6812	3,348	95	80
5920	3,720	6815	4,185	110	90
5927	5,022	6819	5,301	120	95
5932	5,952	6822	6,138	130	100



### Details of the Anchorage Zone for 28 N/mm<sup>2</sup> (cube) / 23 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

Ø 12.9/15.2 mm, Ultimate Load 186/261 kN			
Type	Type	R	As
0.5"	0.6"		
f <sub>pk</sub> 1860	f <sub>pk</sub> 1860		
N/mm <sup>2</sup>	N/mm <sup>2</sup>	mm	mm
5904	6803	750	12.5
5905	6804	750	16.5
5907	6805	750	21.0
5909	6807	750	29.0
5912	6809	900	37.5
5915	6812	1,100	50.0
5920	6815	1,250	62.5
5927	6819	1,500	79.0
5932	6822	1,700	91.5

Ø 15.7 mm, Ultimate Load 279 kN			
Type	R	As	
0.62"			
f <sub>pk</sub> 1860			
N/mm <sup>2</sup>	mm	mm	
6803	800	13.5	
6804	800	18.0	
6805	800	22.0	
6807	800	31.0	
6809	950	40.0	
6812	1,150	53.5	
6815	1,350	67.0	
6819	1,600	85.0	
6822	1,800	98.0	



The radii given in the above tables apply for smooth metal duct. For corrugated metal duct the radius values must be doubled. Ducts need to be pre-bent.

The values for the loop anchorage dimensions are based on European Technical Approval ETA-06/0022.

Application only in concrete members subject to static action. Tendons need to be stressed simultaneously at both ends.

## Bond Head Anchorage HL/HR


HR



	03	04	05	07	09	12	15	19	22		03	04	05	07	09	12	15	19	22
HL	■	■	■	■	■	■	■	■	■	HR	-	■	■	■	■	■	■	■	■

### Technical Data

Type	Ultimate Load		Type	Ultimate Load		HL		HR		HL/ HR
	0.5"	Ø 12.9 mm		0.6"/0.62"	Ø 15.7 mm	A	B	A	B	
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	(186 kN per strand)	f <sub>pk</sub> 1860 N/mm <sup>2</sup>	(279 kN per strand)			mm	mm	mm	mm	mm
-	-	6803	837	290	90	-	-	1,250	1,250	
5904	744	6804	1,116	390	90	210	190	1,250	1,250	
5905	930	6805	1,395	330	90	210	210	1,250	1,250	
5907	1,302	6807	1,953	450	90	250	250	1,250	1,250	
5909	1,674	6809	2,511	390	210	290	290	1,250	1,250	
5912	2,232	6812	3,348	480	250	390	330	1,250	1,250	
5915	2,790	6815	4,185	480	250	410	350	1,250	1,250	
5920	3,720	6819	5,301	610	250	490	390	1,250	1,250	
-	-	6822	6,138	730	250	490	450	1,250	1,250	



ax, ay = minimum centre distance  
rx, ry = minimum edge distance

### Details of the Anchorage Zone for 34 N/mm<sup>2</sup> (cube) / 28 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

HL					
Ø12.9/15.2/15.7mm, Ultimate Load 186/261/279 kN					
Type 0.5"	Type 0.6"/0.62"	Distances of the Anchorages		Additional Reinforcement Helix	
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distances	Edge Distances <sup>1)</sup>	Ø da*	Ø ds*
		mm	mm	mm	mm
5903	6803	180/380	110/210	-	-
5904	6804	190/430	115/235	-	-
5905	6805	210/440	125/240	160	12
5907	6807	230/500	135/270	180	12
5909	6809	280/500	160/270	230	14
5912	6812	300/570	170/305	250	14
5915	6815	350/630	195/335	295	16
5919	6819	390/715	215/380	330	16
5920	6822	410/780	225/410	360	16

1) in case of 30 mm concrete cover

HR					
Ø12.9/15.2/15.7mm, Ultimate Load 186/261/279 kN					
Type 0.5"	Type 0.6"/0.62"	Distances of the Anchorages		Additional Reinforcement Helix	
f <sub>pk</sub> 1860 N/mm <sup>2</sup>	f <sub>pk</sub> 1860 N/mm <sup>2</sup>	Center Distances	Edge Distances <sup>1)</sup>	Ø da*	Ø ds*
		mm	mm	mm	mm
5903	6803	-	-	-	-
5904	6804	285/285	165/165	-	-
5905	6805	305/305	175/175	160	12
5907	6807	340/340	190/190	180	12
5909	6809	375/375	210/210	230	14
5912	6812	390/440	215/240	250	14
5915	6815	460/475	250/260	295	16
5919	6819	525/525	285/285	330	16
5920	6822	570/560	305/300	360	16

1) in case of 30 mm concrete cover

The values for the anchorage zones are based on European Technical Approval ETA-13/0815.


The respective standards and regulations valid at the place of use shall be complied with.

Max. prestressing load 75 % of ultimate load (short-term overstressing to 80 % is permissible).





## Coupler M/ME (Floating Anchorage Block)

### Coupler M




### Coupler ME



### Technical Data

Type	Ultimate Load		Ultimate Load		A	B	C	D	A <sub>D</sub>	B <sub>D</sub>	E
	Ø 15.2 mm	Ø 15.7 mm	(261 kN per strand)	(279 kN per strand)							
f <sub>pk</sub> 1860	(261 kN per strand)	(279 kN per strand)									
N/mm <sup>2</sup>	kN	kN	mm	mm	mm	mm	mm	mm	mm	mm	mm
6801	261	279	98	55	200	20	—	—	—	—	—
6802	522	558	90	105	120	40	60	70	200		
6804	1,043	1,116	130	160	120	55	70	130	650		
6806	1,564	1,674	130	160	120	65	70	130	650		
6808	2,086	2,232	130	210	120	75	70	170	1,050		
6810	2,607	2,790	168	210	120	80	100	170	1,150		
6812	3,129	3,348	168	210	120	80	100	170	1,150		



### Details of Anchorage Zone

**Case 1:** If  $L_R \leq L_2 - \frac{1}{2} \Delta L$   
then  $L = s + 285 \text{ mm} + L_2$

**Case 2:** If  $L_R > L_2 - \frac{1}{2} \Delta L$   
then  $L = s + 285 \text{ mm} + L_2 + \frac{1}{2} \Delta L$

$$s = 0.2 \times \frac{1}{2} \Delta L \geq 120 \text{ mm}$$

Max. prestressing load 70 % of ultimate load (short-term overstressing to 75 % is permissible). The respective standards and regulations valid at the place of use shall be complied with.


### Ø 15.2/15.7 mm, Ultimate Load 261/279 kN

Type	X	Y	Z
0.6"/0.62"			
f <sub>pk</sub> 1860	100	180	60
N/mm <sup>2</sup>	mm	mm	mm
6801	100	180	60
6802	130	155	50
6804	180	195	70
6806	180	195	70
6808	230	195	70
6810	230	235	90
6812	230	235	90

### Block-Out Dimensions

Type	L <sub>2</sub>	L <sub>R</sub>
0.6"/0.62"		
f <sub>pk</sub> 1860	—	—
N/mm <sup>2</sup>	mm	mm
6801	—	—
6802	550	550
6804	700	600
6806	700	600
6808	1,350	600
6810	1,500	800
6812	1,500	800

## Flat Multiplane Anchorage FMA



### Technical Data

Type 0.5"	Ultimate Load <b>Ø 12.9 mm</b> (186 kN per strand)	Type 0.6"/0.62"	Ultimate Load <b>Ø 15.2/15.7 mm</b> (261/279 kN per strand)	A	B	C	D
$f_{pk}1860$ N/mm <sup>2</sup>	(186 kN per strand) kN	$f_{pk}1860$ N/mm <sup>2</sup>	(261/279 kN per strand) kN	mm	mm	mm	mm
5903	558	6802	521	86	160	160	46
5905	930	6804	1,116	86	203	228	46
-	-	6805	1,395	86	268	231	46

### Details of the Anchorage Zone for 25 N/mm<sup>2</sup> (cube) / 20 N/mm<sup>2</sup> (cylinder) Actual Concrete Strength at Stressing

<b>Ø12.9/15.7mm, Ultimate Load 186/265 kN</b>					
Type 0.5"	Distances of the anchorage		Additional Reinforcement Stirrups		
$f_{pk}1860$ N/mm <sup>2</sup>	Center Distance mm	min. slab thickness <sup>1)</sup> mm	a x b mm	n mm	g mm
5903	200	200	180/140	3	12
5905	320	200	230/140	3	12

1) in case of 30 mm concrete cover

<b>Ø15.2/15.7mm, Ultimate Load 279 kN</b>					
Type 0.6"	Distances of the anchorage		Additional Reinforcement Stirrups		
$f_{pk}1860$ N/mm <sup>2</sup>	Center Distance mm	min. slab thickness <sup>1)</sup> mm	a x b mm	n mm	g mm
6802	200	200	160/140	3	12
6804	320	220	230/160	4	12
6805	400	220	310/160	4	12

1) in case of 30 mm concrete cover

Max. prestressing load 75 % of ultimate load (short-term overstressing to 80 % is permissible). The values for the anchorage zones are based on requirements of FIP.


The respective standards and regulations valid at the place of use shall be complied with.

## Equipment Overview

### Jacks



SM 240




HoZ 950/1,700



HoZ 3,000/5,400

Jack Type	59 ..															68 ..																
	01	02	03	04	05	06	07	08	09	12	15	20	27	32	37	01	02	03	04	05	06	07	08	09	10	12	15	19	22	27	31	37
SM 240	x																x															
HoZ 950/100		x	x	x	x												x	x	x													
HoZ 1,700/150						x	x	x	x										x	x	x											
HoZ 3,000/250										x	x										x	x	x	x								
HoZ 5,400/250												x	x								x	x	x	x		x	x	x	x	x	x	
6,800												x	x													x	x	x	x	x	x	
9,750																										x	x					



### Technical Data


Jack Type <sup>1)</sup>	Length L mm	Diameter D mm	Stroke mm	Piston Area cm <sup>2</sup>	Capacity <sup>2)</sup>		Weight kg
					kN	kg	
SM 240	950	98	200	47.13	240	19	
HoZ 950/100	622	203	100	161.98	972	65	
HoZ 1,700/150	858	280	150	298.45	1,745	160	
HoZ 3,000/250	1,130	385	250	508.94	3,054	400	
HoZ 5,400/250	1,215	482	250	894.57	5,367	600	
6,800	1,150	560	300	1237.01	6,803	1,185	
9,750	1,170	680	300	1772.45	9,748	1,770	

1) power seating incl.

2) without friction

## Equipment Overview

### Block-Out-Dimensions



Jack Type	A	B	C	D	E	F	G	H	K	L <sup>2</sup>
SM 240	1,150 <sup>1)</sup>	350	–	80	100	–	70	150	140	500
HoZ 950/100	622	350	–	150	220	–	130	190	260	400
HoZ 1,700/150	858	490	180	–	270	230	170	220	340	600
HoZ 3,000/250	1,130	625	215	–	360	320	220	300	440	600
<b>HoZ 5,400/250</b>	<b>1,215</b>	<b>700</b>	<b>200</b>	<b>300</b>	<b>420</b>	<b>360</b>	<b>270</b>	<b>350</b>	<b>540</b>	<b>800</b>
6,800	1,450 <sup>1)</sup>	–	80	–	–	440	310	490	620	1,200
9,750	1,470 <sup>1)</sup>	–	90	–	–	480	370	550	740	1,200

1) stroke incl.

2) required strand protrusion

Block-Out-Dimensions and strand protrusion apply to jacks with power seating device.

Please contact DSI for dimensions for jacks without power seating device.

## Equipment Overview

### Hydraulic Pumps



77 - 193




R 6.4



R 11.2 - 11.2/210

Pumps	Jacks	SM	HoZ	HoZ	HoZ	HoZ	6,800	9,750
77 - 193		x	x	x				
R 6.4	x	x	x	x				
R 11.2-11.2				x	x	x	x	x
R 11.2-11.2/210					x	x	x	x
ZP 57/28								

for all pushing devices



### Technical Data

Pumps <sup>1)</sup>	Operation Pressure	Capacity V min	eff. Oil Amount	Weight	Dimensions L x W x H
	MPa	l/min	l	kg	mm
77-193	60	3.0	10.0	63	420/380/480
R 6.4	60	06. Apr	70.0	310	1,400/700/1,100
R 11.2-11.2	55 (60)	11.2/22.4	85.0	615	2,000/800/1,000
R 11.2-11.2/210	55 (60)	11.2/22.4	170.0	720	2,000/800/1,300
ZP 57/28	16	53/80	175.0	610	1,260/620/1,330

1) hydraulic pumps will be delivered without oil

## Equipment Overview

### Pushing Equipment



ESG 8 - 1

Type	Tensile or Compressive Force kN	Pushing Speed m/s	Weight kg	Dimensions L x W x H mm	Hydraulic Pumps
ESG 8 - 1	3.9	6.1	140	1,400/350/510	ZP 57/28

### Grouting Equipment (Mixing and Pumping)



MP 2,000 - 5



MP 4,000 - 2



ZMP 712 V

Grouting Equipment	max Injection Pressure MPa	Capacity l/h	Weight kg	Dimensions L x W x H mm
MP 2,000 - 5	1.5	420	300	2,000/950/1,600
MP 4,000 - 2	1.5	1,500	580	2,040/1,040/1,750
ZMP 712 V	4.5	1,500	240	1,220/600/1,475



## Calculation of Elongation

The stressing records are part of the structural design and serve as a basis for the stressing operation. Besides the prestressing data, they contain the sequence of stressing and directives for procedures directly connected with

the stressing operation, such as lowering of the formwork and releasing of bearings.

### Calculation of Strand Tendon Elongation

The total elongation  $\Delta L_{tot}$  which the tendon has to achieve during stressing should be calculated as:


$$\Delta L_{tot} = \Delta L_p + \Delta L_c + \Delta L_{sl} + \Delta L_e$$

$\Delta L_p$  = elongation of the strand tendon [mm]

$$\Delta L_p = \frac{1}{A_p \cdot E_p} \cdot \int_0^{L_p} P_{x,0} \cdot d_x$$

$L_p$  = length of tendon [m]

- $P_{x,0}$  = prestressing force in the tendon at any point at distance  $x$  [kN]  
 $P_{x,0}$  =  $P_0 \cdot e^{-\mu(\hat{\gamma}_x + k \cdot L_p)}$   
 $P_0$  = prestressing force at the stressing anchorage [kN]  
 $\hat{\gamma}_x$  =  $\sum$  angle of planned deflections between the stressing anchorage and any point at distance  $x$  [rad]  
 $\hat{\gamma}_x$  =  $\frac{\pi}{180} \sum_i \sqrt{\alpha_{vi}^2 + \alpha_{hi}^2}$   
 $\alpha_{vi}, \alpha_{hi}$  = vertical and horizontal projections of the angle of i-th deflection [ $^\circ$ ]  
 $\mu$  = friction coefficient [ $\text{rad}^{-1}$ ]  
 $k$  = wobble coefficient [ $\text{rad}/\text{m}$ ]  
 $P_e$  = prestressing force at the stressing anchorage after wedge draw-in [kN]  
 $A_p$  = cross sectional area of prestressing strands



$\Delta L_c$  = elastic deformation of the concrete (shortening must be treated as a positive value) [mm]

$$\Delta L_c = \frac{\sigma_{cm}}{E_c} \cdot L_c$$

$\sigma_{cm}$  = average stress in the concrete cross section at the center of gravity of all tendons due to prestressing force [ $\text{MN}/\text{m}^2$ ]  
 $L_c$  = length of the concrete member [m]

$\Delta L_{sl}$  = sum of anchor plate impressions and wedge draw-in according to the anchorage/coupling type applied [mm]

slip $\Delta L_{sl}$ [mm] anchorage	stressing anchorage	dead end anchorage	bond head anchorage	coupler R	coupler D	coupler M
accessible	1	4	-	-	-	4
not accessible	-	4	-	4	8	-

Values are based on prestressing force acc. to European Technical Approval

$\Delta L_e$  = elongation of the prestressing steel in the jack and seating device (if applicable) [mm]

## Calculation of Elongation

### Calculation of Prestressing Force $P_e$ [kN] at Stressing Anchorage and Influence Length $L_e$ [m]

due to wedge draw-in  $\Delta L_n$  [mm] at stressing anchorage during lock-off of tensioning jack

$$L_e = \sqrt{\frac{\Delta L_n \cdot E_p \cdot A_p}{P_0 \cdot \mu \cdot \gamma_1}}$$

$\gamma_1$  = average angle of deflection along the influence length  $L_e$  of tendon behind the stressing anchorage [rad/m]

$$P_e = P_0 \cdot (1 - 2 \cdot L_e \cdot \mu \cdot \gamma_1)$$

	draw-in slip $\Delta L_n$ [mm]	tendon type	jack type	
			standard case	special case
at the stressing anchorage	6803 - 6837		3*	6**
at the coupler M	6802 - 6812		8	-

values are based on prestressing force acc. to European Technical Approval

\*) with wedge seating    \*\*) without wedge seating

modulus of elasticity [N/mm<sup>2</sup>]

concrete class	C 20/25	C 30/37	C 40/50	C 50/60
$E_{cm}$	29	32	35	37
strand	$E_p = 195,000$ [N/mm <sup>2</sup> ]			

## References

### Bridges




**Westrand Motorway, Amsterdam,  
Netherlands**

**DSI Services:**

- Production
- Supply
- Installation

**DYWIDAG Systems:**

Ø15.7mm St 1860  
DYWIDAG Multistrand Tendons



**Rudavoi Bridge, Federal Road No. 48,  
Cortina d'Ampezzo, Italy**

**DSI Services:**

- Production
- Supply

**DYWIDAG Systems:**

103t of 19-0.6" and 12-0.6", St 1860  
DYWIDAG Multistrand Tendons



**Talbruecke Bergen, A8 Motorway,  
Bergen, Germany**

**DSI Services:**

- Production
- Supply
- Installation

**DYWIDAG Systems:**

500t of Type 19-0.62" Strand Tendons,  
83t of 4-0.62" Monostrand Tendons and  
117t of Wire-EX 66 Tendons

## References

### The Marina Bayfront Bridge, Singapore

#### DSI Services:

- Production
- Supply
- Installation

#### DYWIDAG Systems:

Type 12-0.6" internal, 19-0.6" and 27-0.6" external DYWIDAG Multistrand Tendons



### Jurong East Modification Project, Singapore

#### DSI Services:

- Production
- Supply
- Installation

#### DYWIDAG Systems:

Type 7-0.6", 12-0.6", 19-0.6" and 22-0.6" DYWIDAG Multistrand Tendons with MA Anchorages as well as Ø47mm DYWIDAG Bars



### Kyogbu High Speed Railway, Kimcheon, South Korea

#### DSI Services:

- Production
- Supply
- Technical Support

#### DYWIDAG Systems:

3,168 internal and 1,464 external MA Anchorages Type 22-0.6"; rental of equipment



## References



**St. Anthony Falls Bridge, Minneapolis, Maine, USA**

**DSI Services:**

- Production
- Supply
- Installation
- Engineering Services

**DYWIDAG Systems:**

Supply of 1,300km 0.6" 270k strand tendons; 4,100 Anchorages; 9,000m GEWI® Bars and hardware for formwork  
57,000m 63 mm GEWI® Bars with hardware for reinforcement  
Post-Tensioning installation, stressing, and grouting equipment



**Victory Bridge replacement, Perth Amboy, New Jersey, USA**

**DSI Services:**

- Production
- Supply

**DYWIDAG Systems:**

Supply of 9,168 Anchorages for epoxy-coated strand, 1,126t 0.6" bare and 196t 0.6" epoxy coated strands for strand tendons, 110t DYWIDAG THREADBAR®; rental of technical equipment, stressing and grouting of PT tendons



**The Canada Line, Vancouver/Richmond, British Columbia, Canada**

**DSI Services:**

- Production
- Supply

**DYWIDAG Systems:**

Supply of 374 type 27-0,6", 2,294 type 19-0,6" and 421 type 12-0,6" anchorages and duct; rental of equipment

## References

### Lake Champlain Bridge, Crown Point, New York, USA

#### DSI Services:

- Production
- Supply
- Installation

#### DYWIDAG Systems:

Supply of DYWIDAG Multistrand Tendons for the bridge deck and 64 DYNA Grip® Stay Cables 7-0.6"



### Veterans Memorial Bridge, Portland, Maine, USA

#### DSI Services:

- Production
- Supply

#### DYWIDAG Systems:

Supply of 318 DYWIDAG Strand Tendons, 19-0.6", 196 DYWIDAG Strand Tendons, 27-0.6", with MA Anchorages, 3,000 4-0.6" DYWIDAG Strand Anchors and of 70t of Ø36mm DYWIDAG Post-Tensioning Bars incl. accessories and ducts; rental of equipment



### Highlands-Sea Bright Bridge, Monmouth County, New Jersey, USA

#### DSI Services:

- Production
- Supply
- Technical Support

#### DYWIDAG Systems:

Supply of 615t of types 4-0.6", 12-0.6", 15-0.6", 19-0.6" and 27-0.6" Ø15mm DYWIDAG Multistrand Tendons (120t of which were epoxy coated); 81.5t of Ø36mm (1-3/8") Post-Tensioning Tendons; technical assistance on site



## References

### Commercial Buildings



**Las Vegas CityCenter, Las Vegas,  
Nevada, USA**

**DSI Services:**

- Production
- Supply
- Installation

**DYWIDAG Systems:**

Supply and installation of 33 Type 27-0.6" DYWIDAG Multistrand Tendons, approx. 2,723km (8,883,892ft) of Type 0.6" Strand and approx. 640m (2,100ft) of galvanized 110mm ducts; approx. 610m (2,000ft) of Galvanized Barrier Cable



**Water Tanks, Al Jahra, Kuwait City,  
Kuwait**

**DSI Services:**

- Production
- Supply

**DYWIDAG Systems:**

Supply of 396 6-0.5" DYWIDAG Ring Tendons with anchorages; sale of equipment

## References

---

### Gardens by the Bay, Singapore

#### DSI Services:

- Design
- Production
- Supply
- Installation

#### DYWIDAG Systems:

Supply of Type 0.6" DYWIDAG Multistrand Systems with 12, 15 and 19 strands



### Al Ahwar Complex, Amman, Jordan

#### DSI Services:

- Production
- Supply
- Technical Support

#### DYWIDAG Systems:

Type 3-0.5" and 5-0.5" MA Anchorages; supply of Type SM 240 kN Monostrand Jack and hydraulic pump Type 77-193



### Building Material City (BMC), Abu Dhabi, U. A. E.

#### DSI Services:

- Design
- Production
- Supply
- Installation

#### DYWIDAG Systems:

Supply of 4,700 Type FMA 3-0.5" and 5-0.5" DYWIDAG Flat Multiplane Anchorages



## References

### Tanks



**LNG Tanks, Snøhvit project,  
Melkøya Island, Norway**

**DSI Services:**

- Production
- Supply
- Installation

**DYWIDAG Systems:**

Supply of 1,650t vertical and horizontal DYWIDAG Multistrand Tendons Type 12-0.6" and 22-0.6" MA, St 1860 with accessories



**LNG Tanks, Sagunto, Valencia, Spain**

**DSI Services:**

- Production
- Supply
- Technical Support

**DYWIDAG Systems:**

Supply and installation of 1,300 t of 9- and 19-0.62" DYWIDAG Multistrand Tendons; Supply of 9,312 m GEWI® Threadbars 28 mm with accessories; Rental of technical equipment



**Sewage Plant, Dueren, Germany**

**DSI Services:**

- Production
- Supply
- Installation
- Technical Support

**DYWIDAG Systems:**

Supply and installation of 108t of prefabricated Strand Tendons with 2- to 9-0.6" strands as well as anchorages and anchor plates

## References

### LNG Tanks, Incheon, South Korea

#### DSI Services:

- Production
- Supply
- Technical Support

#### DYWIDAG Systems:

Supply of DYWIDAG Multistrand Tendons with anchorages and accessories, cryogenic GEWI® bars; rental of technical equipment



### LNG Export Terminal, Bal Haf, Yemen

#### DSI Services:

- Production
- Supply

#### DYWIDAG Systems:

Supply of 49,000 m DYWIDAG Multistrand Tendons including anchorages and accessories, 48 t cryogenic GEWI® Threadbars 28mm grade 500/550, 118 t GEWI® Threadbars 32mm grade 500/550



### Qatar Gas II Plant, Ras Laffan , Quatar

#### DSI Services:

- Production
- Supply
- Technical Support

#### DYWIDAG Systems:

Supply of 3,360 t DYWIDAG Multistrand Tendons, type MA 12-0.62" and 9-0.62" ring tendons; rental of technical equipment



## Addresses

### Australia

DYWIDAG-Systems International Pty. Ltd.  
25 Pacific Highway  
Bennetts Green, NSW 2290  
Australia  
Phone +61-2-49 48 90 99  
E-mail dsi@dywidag.com.au  
[www.dsminingproducts.com.au](http://www.dsminingproducts.com.au)

### Austria

DYWIDAG-Systems International GmbH  
Alfred-Wagner-Strasse 1  
4061 Pasching/Linz  
Austria  
Phone +43-7229-610 49 0  
E-mail office@dywidag-systems.at  
[www.dywidag-systems.at](http://www.dywidag-systems.at)

### Belgium

DYWIDAG-Systems International N.V.  
Philippsite 5, bus 15  
Ubicenter  
3001 Leuven  
Belgium  
Phone +32-16-60 77 60  
E-mail info.be@dywidag-systems.com  
[www.dywidag-systems.com](http://www.dywidag-systems.com)

### Brazil

PROTENDIDOS DYWIDAG Ltda.  
Rua Iaiá, 150 – 10º andar – Cj. 102  
Itaim Bibi  
04542-060-São Paulo/SP  
Brazil  
Phone +55-11-21 31 37 00  
E-mail vendas@dywidag.com.br  
[www.dywidag.com.br](http://www.dywidag.com.br)

### Canada

DYWIDAG-Systems International Canada Ltd.  
37 Cardico Drive  
Gormley, ON L0H-1G0  
Canada  
Phone +1-905-888 8988  
E-mail ecd@dsiamerica.com  
[www.dsicanada.ca](http://www.dsicanada.ca)  
  
DYWIDAG-Systems International Canada Ltd.  
19433 – 96th Avenue, Suite 103  
Surrey, BC V4N 4C4  
Canada  
Phone +1-604-888 8818  
E-mail wcd@dsiamerica.com  
[www.dsicanada.ca](http://www.dsicanada.ca)

### Chile

DSI Chile Industrial Ltda.  
Las Encinas #1387, Valle Grande  
Lampa – Santiago  
Chile  
Phone +56-2-596 96 61  
E-mail construcion.chile@dsilatinamerica.com  
[www.dsi-chile.com](http://www.dsi-chile.com)

### China

DYWIDAG-Systems International  
Far East Ltd.  
Room 2306  
CC Wu Building  
302-308 Hennessy Road  
Wanchai  
Hong Kong  
Phone +852-28-33 19 13  
E-mail dsihk@dsife.com.hk

### Colombia

DSI Colombia S.A.S.  
Carrera 43A No. 8 sur – 15 Oficina 403  
Edificio Torre Oviedo  
Medellín, Colombia  
Phone +57-4-403 12 00  
E-mail ventascolombia@dsilatinamerica.com  
[www.dsi-colombia.co](http://www.dsi-colombia.co)

### Croatia

PRESS-KON  
Obala Hrvatskog  
narodnog preporoda 6  
21000 Split  
Croatia  
Phone +385-21-34 27 66  
E-mail info@dywidag-systems.com

### Czech Republic

DYWIDAG-Systems International  
Jilemnického 29/46  
772 00 Olomouc-Nedvězí  
Czech Republic  
Phone +420-585-94 10 76

### Denmark

AAGE CHRISTENSEN A/S  
Skelmosevej 10  
2500 Valby  
Denmark  
Phone +45-36-132 542  
E-mail info@aagechristensen.dk

### Egypt

MISR DYWIDAG  
20 Haroun Street  
El Dokki  
Giza  
Egypt  
Phone +20-2-37 61 48 69  
E-mail mail@misdwywidag.com

### SPENSY

15, Nables St.  
12345 Mohandessin – Giza  
Cairo  
Egypt  
Phone +20-2-33 05 82 20

### Finland

TENSICON OY  
Rattatie 17  
007700, Helsinki 77  
Finland  
Phone +358-500-406 438  
[www.tensicon.fi](http://www.tensicon.fi)

### France

DSI-Artéon SAS  
Rue de la Craz  
Z.I. des Chartinières  
01120 Dagneux  
France  
Phone +33-4-78 79 27 82  
E-mail dsi.france@dywidag.fr  
[www.dywidag-systems.fr](http://www.dywidag-systems.fr)

### Germany

DYWIDAG-Systems International GmbH  
Germanenstrasse 8  
86343 Koenigsbrunn  
Germany  
Phone +49-8231-96 07 0  
E-mail geotechnik@dywidag-systems.com  
[www.dywidag-systems.de](http://www.dywidag-systems.de)

### DYWIDAG-Systems International GmbH

Max-Planck-Ring 1  
40764 Langenfeld  
Germany  
Phone +49-2173-79 02 0  
E-mail suspa@dywidag-systems.com  
[www.dywidag-systems.com/emea](http://www.dywidag-systems.com/emea)

### DYWIDAG-Systems International GmbH

Schuetzenstrasse 20  
14641 Nauen  
Germany  
Phone +49-3321-44 18 0

DYWIDAG-Systems International GmbH  
Siemensstrasse 8  
85716 Unterschleissheim  
Germany  
Phone +49-89-30 90 50 100  
E-mail dsihv@dywidag-systems.com  
[www.dywidag-systems.com](http://www.dywidag-systems.com)

### Greece

Geotechnical Systems  
HELLENPLAN  
4 K. A. Dimitriou Street  
Spata 19004  
Greece  
Phone +30-210-663 57 86

Post-Tensioning Systems  
Kostantinos Zervas  
34th Sintagma Pezikon 5  
Pireas TK 18532 Athens  
Greece  
Phone +30-213-0227 363

Indonesia  
PT DELTA SYSTECH INDONESIA  
Wisma Ritra 2nd Floor  
Jl. Warung Buncit Raya No. 6  
Jakarta – 12740  
Indonesia  
Phone +62-21-797 02 89  
E-mail prestress@dsi-indonesia.co.id

### Israel

EVEN GEV Ltd.  
Emanuel Building  
31 Ha'Barzel Str.  
Ramat Ha'Hayal  
Tel Aviv 69710  
Israel  
Phone +972-77-501 00 56

### Italy

DYWIT S.P.A.  
Viale Europa 72 Strada A 7/9  
20090 Cusago (MI)  
Italy  
Phone +39-02-901 65 71  
E-mail info@dywit.it  
[www.dywit.it](http://www.dywit.it)

### Japan

SUMITOMO ELECTRIC INDUSTRIES, LTD.  
Sales Department  
Special Steel Wire Division  
1-1, Koya-kita Itami,  
Hyogo, 664-0016  
Japan  
Phone +81-72-771-0966

### Korea

DYWIDAG-Systems Korea Co. Ltd.  
5th Floor, Spring Morning B/D  
8, Mabang-ro, Seocho-gu  
Seoul 137-894  
Korea  
Phone +82-2-34 72 01 41  
E-mail dywidagkor@gmail.com  
[www.dsikorea.co.kr](http://www.dsikorea.co.kr)

### Lebanon

SOPREL Liban SAL  
Liban Cable Street  
Halate  
Lebanon  
Phone +961-9-44 88 60  
E-mail contact@soprel-liban.com

### Lithuania

Delta Nova  
Užupio g. 30  
LT-01203 Vilnius  
Lithuania  
Phone +370-5272-53 08  
E-mail info@deltanova.lt  
[www.deltanova.lt](http://www.deltanova.lt)

## Addresses

### Mexico

DS International México, S.A. de C.V.  
Av. Aviación No 1002 Bod. 15  
Parque Industrial FERRAN I  
San Juan de Ocotán  
Zapopan, Jalisco 45019  
México  
Phone +52-33-66 57 94  
E-mail dsimexico@dsiunderground.com  
www.dsiunderground.com

### Netherlands

DYWIDAG-Systems International B.V.  
Veilingweg 2  
5301 KM Zaltbommel  
Netherlands  
Phone +31-418-57 89 22  
E-mail email@dsi-nl.nl  
www.dywidag-systems.com

### Nigeria

PTSL Post Tensioning Services Limited  
167C Isale Eko Av  
Dolphin Estate  
Ikoyi, Lagos  
Nigeria  
Phone +234-80-72 72 22 22  
E-mail info@pts-l.com  
www.pts-l.com

### Norway

Dywidag Norge AS  
Norvald Strands veg 21  
2206 Kongsvinger  
Norway  
Phone +47-67-06 15 60  
E-mail adm@dywidag-norge.no  
www.dywidag-norge.no

### Peru

DSI Peru S.A.C.  
Calle Uno Oeste 0061 Of. 103  
San Isidro-Lima 1 / Peru  
Phone +51-1-224 54 54  
E-mail construccion.peru@dsilatinamerica.com  
www.dsi-peru.com

### Poland

DYWIDAG-Systems International Sp. z o.o.  
ul. Bojowników o Wolnos' c' i Demokracje, 38/121  
41-506 Chorzów  
Poland  
Phone +48-32-241 09 98  
E-mail dsi-polska@dywidag-systems.com  
www.dywidag-systems.pl

### Portugal

DYWIDAG SISTEMAS CONSTRUCTIVOS, SA  
Rua D. Manuel, n.º 24 A  
Quinta da Parreirainha  
2695-003 Bobadela (Loures)  
Portugal  
Phone +351-21-892 28 90  
E-mail dywidag@dywidag-sistemas.com

### Qatar

QACS (Qatar Australien Construction Systems W.L.L.)  
Al Thumama  
Street No 911, Villa No 56, Area No 46  
E Ring road, Near to Electric  
Doha / Qatar  
Phone +974-44-58 04 11

### Russia

DSI-PSK OOO  
Joint Venture  
Leninsky prospekt,  
d. 105, korp. 4  
Moscow 119421  
Russia  
Phone +7-495-234 25 02  
www.psk-holding.ru

### Saudi Arabia

DYWIDAG-Systems International „DSI“, Riyadh  
P.O. Box 53039,  
Riyadh, 11583  
Saudi Arabia  
Phone +966-1-46 50 311 ext. 106

BIC Prestressed Concrete  
P.O. Box 101688,  
Riyadh, 11665  
Saudi Arabia  
Phone +966-1-278 14 79  
E-mail info@bic-ksa.com  
www.bic-ksa.com

**Serbia & Montenegro**  
EnCon d.o.o.  
3, Cara Lazara Street  
11000 Belgrade  
Serbia & Montenegro  
Phone +381-11-328 12 73

### Singapore

UTRACON STRUCTURAL SYSTEMS PTE LTD  
7 E Pioneer Sector 1  
Singapore 628446  
Phone +65-64-15 30 78  
E-mail ultracon@utracon.com  
www.utracon.com

### Slovakia

Doprastav, a.s.  
Závod Prefa  
Drien'ová 31  
821 01 Bratislava  
Slovakia  
Phone +421-2-48 271 130

### South Africa

Amsteelo Systems  
Unit 20, Lothlorien Industrial Park  
Tedstone Road, Wadeville  
Albemarle 1410  
South Africa  
Phone +27-11-827 6721

### Spain

DYWIDAG SISTEMAS CONSTRUCTIVOS, S.A.  
Avd/de la Industria, 4  
Pol. Ind. la Cantuena  
28947 Fuenlabrada (Madrid)  
Spain  
Phone +34-91-642 20 72  
E-mail dywidag@dywidag-sistemas.com  
www.dywidag-sistemas.com

### Switzerland

SpannStahl AG  
Industriegebiet  
Waesseristrasse 29  
8340 Hinwil/ZH  
Switzerland  
Phone +41-44-9 38 97 97  
E-mail info@spannstahl.ch  
www.spannstahl.ch

### Taiwan

DYWITECH Co. Ltd.  
13th Fl.-3, No. 163, Sec. 1, Keelung Road  
Taipei 110  
Taiwan, R.O.C.  
Phone +886-2-27 48 10 76

### Thailand

D-Tech Postten Co., Ltd.  
91/22 Suwinthawong road  
Minburi district, Minburi  
Bangkok 10510  
Thailand  
Phone +66-2543-77 61

### Turkey

DIVIGER Yapı Teknoloji A.S.  
Yıldız Posta Cad.  
Aylıdz Sitesi 30/15  
34349 İstanbul-Gayrettepe  
Turkey  
Phone +90-212-234 56 12  
E-mail diviger@diviger.com

### United Kingdom

DYWIDAG-Systems International Ltd.  
Northfield Road  
Southam, Warwickshire, CV47 0FG  
Great Britain  
Phone +44-1926-81 39 80  
E-mail sales@dywidag.co.uk  
www.dywidag.co.uk

### USA

DYWIDAG-Systems International USA Inc.  
320 Marmon Drive  
Bolingbrook, IL 60440  
USA  
Phone +1-630-739 1100  
E-mail dsiamerica@dsiamerica.com  
www.dsiamerica.com

DYWIDAG-Systems International USA Inc.  
2154 South Street  
Long Beach, CA 90805  
USA  
Phone +1-562-531 6161  
E-mail dsiamerica@dsiamerica.com  
www.dsiamerica.com

**North America**

DYWIDAG-Systems International USA Inc.  
320 Marmon Drive  
Bolingbrook, IL 60440  
USA  
Phone +1-630-7 39 11 00  
E-mail [dsiamerica@dsiamerica.com](mailto:dsiamerica@dsiamerica.com)  
[www.dsiamerica.com](http://www.dsiamerica.com)

**South America**

PROTENDIDOS DYWIDAG Ltda.  
Rua Iaiá, 150 – 10º andar - Cj.102  
Itaim Bibi  
04542-060-São Paulo/SP  
Brazil  
Phone +55-11-21 31 37 00  
E-mail [vendas@dywidag.com.br](mailto:vendas@dywidag.com.br)  
[www.dywidag.com.br](http://www.dywidag.com.br)

**EMEA**

DYWIDAG-Systems International GmbH  
Max-Planck-Ring 1  
40764 Langenfeld  
Germany  
Phone +49-2173-79 02 00  
E-mail [suspa@dywidag-systems.com](mailto:suspa@dywidag-systems.com)  
[www.dywidag-systems.com/emea](http://www.dywidag-systems.com/emea)

**APAC**

DYWIDAG-Systems International Pty. Ltd.  
25 Pacific Highway  
Bennetts Green, NSW 2290  
Australia  
Phone +61-2-49 48 90 99  
E-mail [dsi@dywidag.com.au](mailto:dsi@dywidag.com.au)  
[www.dsminingproducts.com.au](http://www.dsminingproducts.com.au)

**Please Note:**

This brochure serves basic information purposes only. Technical data and information provided herein shall be considered non-binding and may be subject to change without notice. We do not assume any liability for losses or damages attributed to the use of this technical data and any improper use of our products. Should you require further information on particular products, please do not hesitate to contact us.

ARGENTINA  
AUSTRALIA  
AUSTRIA  
BELGIUM  
BOSNIA AND HERZEGOVINA  
BRAZIL  
CANADA  
CHILE  
CHINA  
COLOMBIA  
COSTA RICA  
CROATIA  
CZECH REPUBLIC  
DENMARK  
EGYPT  
ESTONIA  
FINLAND  
FRANCE  
GERMANY  
GREECE  
GUATEMALA  
HONDURAS  
HONG KONG  
INDONESIA  
ITALY  
JAPAN  
KOREA  
LEBANON  
LUXEMBOURG  
MALAYSIA  
MEXICO  
NETHERLANDS  
NORWAY  
OMAN  
PANAMA  
PARAGUAY  
PERU  
POLAND  
PORTUGAL  
QATAR  
RUSSIA  
SAUDI ARABIA  
SINGAPORE  
SOUTH AFRICA  
SPAIN  
SWEDEN  
SWITZERLAND  
TAIWAN  
THAILAND  
TURKEY  
UNITED ARAB EMIRATES  
UNITED KINGDOM  
URUGUAY  
USA  
VENEZUELA

[www.dywidag-systems.com/emea](http://www.dywidag-systems.com/emea)